

JS005993543A

United States Patent [19]

Aoki et al.

[11] Patent Number:

5,993,543

[45] Date of Patent:

Nov. 30, 1999

[54] METHOD OF PRODUCING PLASMA DISPLAY PANEL WITH PROTECTIVE LAYER OF AN ALKALINE EARTH OXIDE

[75] Inventors: Masaki Aoki, Mino; Hideo Torii, Higashiosaka; Eiji Fujii, Hirakata; Mitsuhiro Ohtani, Sakai; Takashi Inami, Suita; Hiroyuki Kawamura, Katano; Hiroyoshi Tanaka, Kyoto; Ryuichi Murai, Toyonaka; Yasuhisa Ishikura, Katano; Yutaka Nishimura, Kadoma; Katsuyoshi Yamashita, Katano, all of Japan

[73] Assignee: Masaki Aoki Et Al., Japan

[21] Appl. No.: 08/890,577

[22] Filed: Jul. 9, 1997

Related U.S. Application Data

[62] Division of application No. 08/766,030, Dec. 16, 1996, Pat. No. 5,770,921.

[30]	For	eign Appl	licati	ion Priority I)ata		
Fel Jun.	15, 1995 b. 1, 1996 24, 1996 26, 1996	[JP] Ja [JP] Ja	ipan ipan			8-01632 8-16263	6
[51] [52]	Int. Cl. ⁶ U.S. Cl.	•••••		C30B 29/1	16; C30 7/101; :	B 23/0	0
[58]	Field of	Search 117/1		103, 104, 944	117/3	, 88, 92),

[56] References Cited

U.S. PATENT DOCUMENTS

4,584,086 4/1986 5,458,086 10/1995 5,604,396 2/1997 5,818,168 10/1998	Yamashita et al. 313/587 Hayakawa et al. 204/429 Smith et al. 117/200 Watanabe et al. 313/485 Ushifusa et al. 313/582 Tanabe et al. 313/506
--	---

FOREIGN PATENT DOCUMENTS

279744	8/1988	European Pat. Off
649159	4/1995	European Pat. Off
5234519	10/1993	Japan.
5342991	12/1993	Japan .
6342631	12/1994	Japan .
2109628	6/1983	United Kingdom .
9519027	7/1995	WIPO.

OTHER PUBLICATIONS

"E-Beam Evaporated Glass and MgO Layers for Gas Panel Fabrication," by K.C. Park et al., IBM J. Res. Develop., vol. 22, No. 6, Nov. 1978.

"Fluorescent Substance for Color Plasma Display Panel," by J. Koike, O Plus E, No. 195, 1996.

"Low-Voltage Operated AC Plasma-Display Panels", by T. Shinoda et al., IEEE Transactions on Electron Devices, vol. ED-26, No. 8, Aug. 1979.

Primary Examiner—Felisa Hitesher Assistant Examiner—Donald L. Champagne Attorney, Agent, or Firm—Price, Gess & Ubell

[57] ABSTRACT

The first object of the present invention is to provide a PDP with improved panel brightness which is achieved by improving the efficiency in conversion from discharge energy to visible rays. The second object of the present invention is to provide a PDP with improved panel life which is achieved by improving the protecting layer protecting the dielectrics glass layer. To achieve the first object, the present invention sets the amount of xenon in the discharge gas to the range of 10% by volume to less than 100% by volume, and sets the charging pressure for the discharge gas to the range of 500 to 760 Torr which is higher than conventional charging pressures. With such construction, the panel brightness increases. Also, to achieve the second object, the present invention has, on the surface of the dielectric glass layer, a protecting layer consisting of an alkaline earth oxide with (100)-face or (110)-face orientation. The protecting layer, which may be formed by using thermal Chemical Vapor Deposition (CVD) method, plasma enhanced CVD method, or a vapor deposition method with irradiation of ion or electron beam, will have a high sputtering resistance and effectively protect the dielectrics glass layer. Such a protecting layer contributes to the improvement of the panel life.

27 Claims, 9 Drawing Sheets

